



CoFeV49%/7.80

Density	7.80 gcm ⁻³ min.
B – 1 kAm ⁻¹ (13 Oe)	1.86 T (18,600 G)
B – 5 kAm ⁻¹ (63 Oe)	2.09 T (20,900 G)
B – 10 kAm ⁻¹ (126 Oe)	2.14 T (21,400 G)
B – 150 kAm ⁻¹ (1885 Oe)	2.36 T (23,600 G)

J _{sat}	2.20 T (22,000 G)
Max permeability	3200
Remanence (B _r)	1.40 T (14,000 G)
Coercivity (H _c)	240 Am ⁻¹ (3 Oe)
Resistivity (Typical)	50 μΩ cm

